

NORTHWEST TESTING LABORATORIES, INC.

CONSTRUCTION INSPECTION
MATERIALS INSPECTION
CHEMICAL ANALYSIS
PHYSICAL TESTING

5405 N. Lagoon Avenue
P.O. Box 17126
Portland, Oregon 97217-0126
Phone: (503) 289-1778
FAX: 289-1918

NON-DESTRUCTIVE TESTING
WELDING CERTIFICATION
SOIL TESTING
ASSAYING

July 2, 1990

Superior Products
J.E. Pritchett
P.O. Box 2357
Salina, Kansas 67402-2357

Subject: Salt Spray Corrosion tests conducted on specimens submitted.

Report:

Item: 4 x 12" Coated Test Panels

Coating Type: White Super Therm

Test: Salt Spray (Fog) Testing

Method: ASTM B117

Test Parameters:


Chamber Temperature	35°C (95°F)
Salt Solution, %	5% ±1%
pH	6.9
Flow	1.4 ml/hour
Total Exposure	450 Hours

This report is to certify that the above listed items submitted had been subjected to 450 hours of salt spray exposures in accordance with ASTM B117.

Evaluation: ASTM D1654

Rating Procedure B 9

Respectfully,
NORTHWEST TESTING LABORATORIES, INC.


Paul Irish, Technical Director

Report Number: 336033

MAR 20 1995